

Laurenco PPC Membrane

(Premium Protection Course)
Product #: A7460

Product Data Sheet

Physical Properties (ASTM D5147):	Test Results	ASTM D6163 Minimum Standard
Tensile Strength (lbf/in), 0°F (MD/XMD)	114/99 lbf/in	70 lbf/in
Tensile Strength (lbf/in), 73°F (MD/XMD)	103/74 lbf/in	50 lbf/in
Elongation (% @ Max Load), 0°F, (MD/XMD)	45/59%	20%
Elongation (% @ Max Load), 73°F (MD/XMD)	54/61%	35%
Elongation (% @ 5% Max Load), 73°F (MD/XMD)	57/68%	35%
Tear Strength (lbf), (MD/XMD), 73°F, minimum	115/92 lbf	55 lbf
Low Temperature Flexibility, (°F), maximum	0°F (-18°C)	0°F
Dimensional Stability, %, maximum	<0.2%	1%
High Temperature Stability, (°F)	250°F (121°C)	215°F

Laurenco PPC is a resilient smooth surfaced, premium polymer modified adhesively applied protection sheet. Manufactured with a fiberglass mat that is saturated and coated with high quality, asphaltic bitumen and polymer modifiers for a durable, flexible and easily applied protection sheet. It is designed for use with the Laurenco Waterproofing System as a protection course.

Product Name: Laurenco PPC

Classification: Polymer Modified Protection Sheet

Application Method: Laurenco PPC is applied using Laurenco Adhesive.

Approvals: Meets ASTM D 6163 Type I, Grade S. Laurenco SPC is UL Classified with Underwriter's Laboratories (UL), is Factory Mutual (FM) Approved, listed with Florida Building Code and Miami Dade County Code Compliance.

Contact Laurenco for specific/applicable codes.

Product Data: Laurenco PPC (typical)

Thickness: 3.0 mm (120 mils)

Weight: 86 lbs./roll (40 kg/m²)

Roll Dimensions: 39 3/8" x 32' 9" (1m x 10m).



P.O. Box 599 - Mars, PA 16046
800-321-3337

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by “in-house” and independent “third party” evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer’s representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY FBC CHEMICAL CORP. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Laurenco products are manufactured by FBC Chemical Corp.



EXCELLENCE IN WATERPROOFING
SINCE 1955 —