

Laurenco G FR CAP

Product #: A7480

Product Data Sheet

Physical Properties ASTM D 6164 Type 1

<u>Test Method</u>	<u>Property</u>	<u>Typical</u>
ASTM D5147	Thickness, typical, mm (mils)	4.0 (160)
ASTM D 5147	Peak Load @ 23 +/- 2°C (73.4 +/- 3.6° F), MD and XMD, min, kN/m (lbf/in.)	8.8 (50)
ASTM D 5147	Elongation @ 23 +/- 2°C (73.4 +/- 3.6° F), MD and XMD, min (%)	35
ASTM D 5147	Tear Strength @ 23 +/- 2°C (73.4 +/- 3.6° F), min, N (lbf)	246 (55)
ASTM D 5147	Low Temperature Flexibility, max, °C (°F)	-18 (0)
ASTM D 5147	Granule Embedment, g	2

Available Colors

Top surface granule protection is available in white as standard: Colors available as special order are: Black and Grey. Laurenco G FR CAP membranes are fire rated, high quality elastomeric, polymer modified asphalt roofing membranes specially designed for cold adhesive applications when UV protection is required for the Laurenco Waterproofing System. Reinforced with a superior polyester membrane, the Laurenco G-CAP FR exhibits exceptional tensile strength and puncture resistance. The granulated surface provides superior long term UV protection. Manufactured specifically for use with the Laurenco Waterproofing System, the proprietary polymer modified asphalts and product composition will offer long term resistance to moisture, dimensional stability and flexibility.

The top surface of Laurenco G FR CAP membrane has a granular finish available in white (standard) with other colors available as special order. The membrane is free of granules along the selvage edge.



P.O. Box 599 - Mars, PA 16046
800-321-3337

Product Name: Laurenco G FR CAP

Classification: Polymer Modified Granulated Cap Sheet

Application Method: Laurenco G FR CAP is applied using Laurenco Adhesives and Cements.

Approvals: Meets ASTM D 6164 Type 1
Contact Laurenco for specific/applicable codes.

Product Data: Laurenco G FR CAP (Typical)

Thickness: 4.0 mm (160 mils)

Weight: 103lbs.

Roll Dimensions: 39'10" x 39- $\frac{3}{8}$ " (10m x 1m).

Rolls per Pallet: 20

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY FBC CHEMICAL CORP. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Laurenco products are manufactured by FBC Chemical Corp.



EXCELLENCE IN WATERPROOFING
SINCE 1955 —